

ESTUCADO RECICLADO MATE

100% RECICLADO

Propiedad	Unidad	Norma	Parámetros						
Gramaje	g/m ²	ISO 536	60	65	70	80	90	100	115
Blancura	%	ISO 2470	82	84	84	84	84	84	84
Opacidad	%	DIN 53146	≥ 92	≥ 92	≥ 92	≥ 94	≥ 94	≥ 94	≥ 94
Brillo	%	ISO 8254-1	15-25	15-25	15-25	15-25	15-25	15-25	15-25
Volumen	cm ³ /g	EN 20534	1.1	1.1	1.1	1.1	1.1	1.1	1.1
	μm		66	72	77	88	99	110	126

